

Requirement guidelines for the awarding of the EMICODE ligence

The product mentioned on the front side of the licence has to fulfil among others the following criteria in accordance with the Constitution and the guidelines of the Technical Advisory Board of the GEV:

- The product meets all the legal requirements, especially the chemical laws and their specifications.
- The product is solvent free as specified in clause 2.4 of the "GEV Classification Criteria", except if it is a surface treatment product. If the product is assigned to a GISCODE product group then this can be labelled.
- A safety data sheet (SDS) according to local law in its respectively valid version is issued for the product.
- Carcinogenic, mutagenic, reprotoxic substances of the categories 1A or 1B are not added during the manufacture of the product.
- The testing of the product is performed in accordance with the GEV Testing Method. VOC determination is performed in a test chamber followed by the Tenax / thermal desorption procedures with subsequent GC/MS analysis.
- The assignment of an EMICODE class is performed according to the following criteria and TVOC/TSVOC concentration levels. The corresponding EMICODE class shall be used to label the product:

1) Installation products, adhesives and construction products

/	/			
Parameter	EC 1 ^{PLUS}	₩€ C 1	EC 2	
Faiallete	max. allowed concentration [µg/m³]			
TVOC after 3 days	<u>≤</u> 750	<u> </u>	<u><</u> 3000	
TVOC after 28 days	<u>≤</u> 60	<u>< 100 </u>	<u><</u> 300	
TSVOC after 28 days	<u>≤</u> 40	<u>≥</u> 50		
R value based on German AgBB LCI (NIK) after 28 days	1) -	-	
Sum of non-assessable VOC	<u>≤</u> 40		-	
Formaldehyde after 3 days	<u>≤</u> 50	<u><</u> 50	<u><</u> 50	
Acetaldehyde after 3 days	₹50	<u><</u> 50	<u><</u> 50	
Sum of form and acetaldehyde	<u>≤</u> 0.05 ppm	<u><</u> 0.05 ppm	<u><</u> 0.05 ppm	
Sum of volat le C1A/C1B after 3 days	<u><</u> 10	<u><</u> 10	<u><</u> 10	
Any volatile C1A/C1B after 28 days	<u>≤</u> 1 / /	<u><</u> 1	<u><</u> 1	

2) Products for floor surface treatments for parquet, mineral floors and resilient floorings

	Person etch	EC 1PLUS	EC 1	EC 2
	Parameter	max. allowed concentration [µg/m³]		
	Sum TVOC + TSVOC after 28 days	≤ 100 thereof max. 40 SVOC	≤ 150 thereof max. 50 SVOC	\leq 450 thereof max. 100 SVOC
	Formaldehyde after 3 days	<u><</u> 50	<u><</u> 50	<u><</u> 50
\setminus	Acetaldehyde after 3 days	<u><</u> 50	<u><</u> 50	<u><</u> 50
	Any volatile C1A/C1B after	<u><</u> 10	<u><</u> 10	<u><</u> 10
	Any volatile C1A/C1B after 28 days	<u><</u> 1	<u><</u> 1	<u><</u> 1