

ECORAPID INDUSTRY

single-component/two-component acrylic-polyurethane water bottom with very fast drying for wooden floors



Description

ECORAPID INDUSTRY is a single-component/two-component acrylic-polyurethane water-based primer for industrial use, specific for the first coat of laquer cycles for floors and wooden products; has excellent physical-chemical characteristics such as: high dry residue and transparency, fast drying, easy sanding.

Characteristics

Mixture ratio	single-component/two-component (10:1)
Application temperature	+10°C ÷ +25°C
Application	Spray
Thinning (if necessary)	DILUENTE DR H2O
Coverage	70-100 g/m ²
Dust dry	20' ⁽¹⁾
Fingerprint dry	40' ⁽¹⁾
Sanding	12 h ⁽¹⁾
Overcoating without sanding	1-12 h ⁽¹⁾
Wood oxidation	low
Pore filling	good
Storage stability	1 year ⁽²⁾
Packaging	5 L - 10 L - 25 L
Tool cleaning	DILUENTE DNH 40 (with fresh product)

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

ECORAPID INDUSTRY can be applied with curtain coater or by means of manual and/or mechanical spraying systems. ECORAPID INDUSTRY is applied on wooden floors previously grouted, sanded and carefully vacuumed. After less than 2 hours from application (without sanding) or after a longer time interval (in this case sanding with 220 grit paper) apply the second coat of ECORAPID INDUSTRY or directly the finish using: ECOWOOD 2K INDUSTRY or ECOCLASS (see relative data sheets).

Notes:

It is possible to mix ECORAPID INDUSTRY with 10% of INDURITORE UW/110 or INDURITORE UW/330.

Label elements

· Causes serious eye irritation.

· Wash thoroughly with water after use. · Wear protective gloves / protective clothing / eye protection / face protection. · IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. · If eye irritation persists: Get medical advice / attention.



These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.