

Technical Datasheet

Item Code: VEUV153X | Rev.: 28-10-2021 | Ver: 3.1

FINITURA UV R77

UV Lacquer based on special acrylic resins



¤Description

Single-component photoactivated product based on special acrylic resins, used as a finishing coat for matte effect for varnishing of wooden floors, furniture, doors and panels. It's characterized by excellent hardness, thermal expansion, uniformity and flexibility.

¤Characteristics

Preparation	photoactivated
Thinning (if necessary)	DILUENTE MONOMERICO
Application temperature	+10°C ÷ +25°C
Viscosity	40" - 50" Ford Cup 6
Application	single head roller coater / twin
	head roller coater / engraved roller
Coverage	7/15 g/m²
Flash-Off	n.a.
Hardening	2/3 mercury lamps 80W cm²
Gloss level	5 gloss
Dry residue	99%
Chemical and physical	excellent
characteristics	
Storage stability	1 year ⁽¹⁾
Packaging	25 KG
Machine cleaning	DILUENTE ACETONE

in original sealed containers at temperatures between +10°C and +25°C

¤How to use

FINITURA UV R77 is a UV finisher suitable for application by roller machine such as baby and roller laser. FINITURA UV R77 is generally applied on wooden floors previously treated with apposite primers. The regular and intense maintenance of wooden floors treated with FINITURA UV R77 should be made with the VELUREX products line (see technical data sheet).

¤Label elements

· Causes serious eye damage.· Causes skin irritation.· May cause an allergic skin reaction.· Very toxic to aquatic life.· Toxic to aquatic life with long lasting effects.

· IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Wear protective gloves/protective clothing/eye protection/face protection.· Immediately call a POISON CENTER or doctor / physician.· Avoid release to the environment.· Collect spillage.

Contents:DIACRILATO DI OSSIBIS (METIL- 2,1- ETANDIILE) GLICEROLO, PROPOSSILATO,ESTERI CON ACIDO ACRILICO 1.6-ESANDIOL DIACRILATO;



These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.