

# FINITURA UV R78

UV Lacquer based on special acrylic resins



## Description

Single-component photoactivated product based on special acrylic resins, used as a finishing coat applied by roller coater for varnishing of wooden floors, furniture, doors and panels. It's characterized by excellent hardness, thermal expansion, uniformity and flexibility.

## Characteristics

Preparation	photoactivated
Thinning (if necessary)	DILUENTE MONOMERICO
Application temperature	+10°C ÷ +25°C
Viscosity	26" - 30" Ford Cup 6
Application	single head roller coater / twin head roller coater / engraved roller
Coverage	7-15 g/m <sup>2</sup>
Flash-Off	n.a.
Hardening	2/3 mercury lamps 80 W cm <sup>2</sup>
Gloss level	10 gloss - 50 gloss
Dry residue	99%
Specific weight	1,05 Kg/L
Chemical and physical characteristics	excellent
Storage stability	1 year <sup>(1)</sup>
Packaging	25 KG
Machine cleaning	DILUENTE ACETONE

1 in original sealed containers at temperatures between +10°C and +25°C

## How to use

FINITURA UV R78 is a UV top coat suitable for application by roller machine such as baby and roller laser. FINITURA UV R78 is generally applied on wooden floors previously treated with apposite primers. The regular and intense maintenance of wooden floors treated with FINITURA UV R78 should be made with suitable product from VELUREX range.

## Label elements

· Causes serious eye irritation.· Causes skin irritation.· May cause an allergic skin reaction.· Toxic to aquatic life with long lasting effects.

· Wash thoroughly with water after use.· Avoid release to the environment.· Wear protective gloves / protective clothing / eye protection / face protection.· IF ON SKIN: Wash with plenty of soap and water.· If skin irritation or rash occurs: Get medical advice / attention.

Contents: 1,6-HEXANEDIOL DIACRYLATE; TRIMETHYLOLPROPANE TRIACRYLATE; 2-(2-ETHOXYETHOXY)ETHYL ACRYLATE; TRI (PROPYLENE GLYCOL) DIACRYLATE, MIXTURE OF ISOMERS;



These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.