

FONDO FOW R700

One-component, fast-drying water bottom for wood floor roller coater application



Description

FONDO FOW R700 is a single-component polyurethane water primer for roller applications, specific for the first coat of parquet and wood painting cycles in general. FOW R700 has high dry residue, fast drying, easy sanding. In addition, it gives the wood a warm tone, especially on oak wood, as well as a pleasant aesthetic appearance.

Characteristics

| | |
|-------------------------|--------------------------------------|
| Mixture ratio | single-component |
| Application temperature | +10°C ÷ +25°C |
| Application | roller coater |
| Thinning (if necessary) | DILUENTEDR H2O |
| Coverage | 30-50 g/m ² |
| Dust dry | 20' ⁽¹⁾ |
| Fingerprint dry | 40' ⁽¹⁾ |
| Sanding | 12 h ⁽¹⁾ |
| Wood oxidation | low |
| Pore filling | good |
| Storage stability | 1 year ⁽²⁾ |
| Packaging | 25 Kg |
| Tool cleaning | DILUENTE DNH 40 (with fresh product) |

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

FONDO FOW R700 is a high viscosity primer for general use, suitable for roller applications. FONDO FOW R700 is applied on a wooden floor previously stuccoed, sanded with 120-150 paper and carefully vacuumed. After drying and sanding apply our single/two-component water laquer or our FINITURA UW R800 (see the relevant data sheet).

Notes:

The sanding of FONDO FOW R700 must be carried out in a uniform way to avoid uneven color variations.

Label elements

· Causes serious eye irritation.

· Wash thoroughly with water after use. · Wear protective gloves / protective clothing / eye protection / face protection. · IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. · If eye irritation persists: Get medical advice / attention.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.