

# ANTICANTE WEST

## Ageing and smoothing powder - OLD WEST



### Description

ANTICANTE WEST is an ageing and smoothing powder, water dispersible, in order to obtain an enhanced vintage effect like patina.

### Characteristics

Application temperature	+10°C ÷ +25°C
Application	spray
Coverage	40-60 g/m <sup>2</sup>
Thinning (if necessary)	water
Overcoating without sanding	4 h <sup>(1)</sup>
Storage stability	1 year <sup>(2)</sup>
Packaging	1 Kg - 5 Kg
Tool cleaning	water

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

### Available Versions

ANTICANTE WEST B: powder to obtain old grey effects.  
 ANTIKANTE WEST C: whitening powder to enhance the "white-old" effect.

### How to use

ANTICANTE WEST has to be applied on woods that have been filled, sanded and previously treated with ATTIVATORE WEST and/or CONVERTITORE WEST (see technical data sheets).

Mix ANTIKANTE WEST in water in a percentage between 3% and 15%, then apply ANTIKANTE WEST by spraying following the quantity reported (40-60 g/m<sup>2</sup>).

Let the product reacts at least for 4 hours, after the complete drying, rub the surface with a red scotch brite and then apply FONDO FOW 100, PRYMER PRIMA PATINA or PRYMER PRIMA PATINA ANTIKANTE (see technical data sheets). Check the complete drying before the application of another coat of product.

**ATTENTION:** do not mix different ANTIKANTE WEST together.

#### NOTES:

ANTICANTE WEST B / C: can be diluted in all the ATTIVATORE WEST range of products and CONVERTITORE WEST 6.

**Due the high variability of the OLD WEST effects from: different dilution, taylormade cycles, different reaction time-schedules, different wood, quantity applied, etc. CHIMIVER PANSERI S.p.A. will not respond to any claim, if it will not provide the reproducibility of the OLD WEST cycle applied, as reported on the technical data sheet of each product.**

### Label elements

· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.