

# CHIM TABU FD

**Two-component aliphatic polyurethane not yellowing primer**



## Description

CHIM TABU FD is a two-component aliphatic polyurethane primer with special UV ray-absorbing elements. It is non-yellowing and features surface hardness and transparency.

## Characteristics

Mixture ratio	25% INDURITORE N.I. 600 U
Application temperature	+10°C ÷ +25°C
Application	roller 6-8 mm / brush
Thinning (if necessary)	DILUENTE DMC 50
Coverage	100 g/m <sup>2</sup>
Dust dry	30' <sup>(1)</sup>
Fingerprint dry	2 h <sup>(1)</sup>
Pot-Life	3-4 h <sup>(1)</sup>
Sanding	24 h <sup>(1)</sup>
Overcoating without sanding	n.a.
Wood oxidation	marked
Pore filling	good
Storage stability	1 year <sup>(2)</sup>
Packaging	12,5 L (10 + 2,5)
Tool cleaning	DILUENTE DNE

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

## Available Versions

**STD:** transparent to keep the wood natural.

**COLORATO:** colored in order to change the wood color.

## How to use

Shake well before use.

Catalyze CHIM TABU FD comp. A with INDURITORE NI 600 U (ratio 4:1). Then dilute with DILUENTE DMC 50 in the proportion of 25% of CHIM TABU FD comp. A. CHIM TABU FD may be applied over a coat of CHIM TABU PRYMER or over a sanded and carefully vacuumed wooden floor. Sanding with 150/180-grit sandpaper must precede a subsequent finishing coat of CHIM TABU FT.

## Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

## Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



[http://www.chimiver.com/tds/EN\\_CHIM\\_TABU\\_FD.pdf](http://www.chimiver.com/tds/EN_CHIM_TABU_FD.pdf)