Chimiver®
"Your floors partner"

Technical Datasheet

Item Code: CTAB030A | Rev.: 17-07-23 | Ver: 3.4

CHIM TABU INDUSTRIA

Two component solvent based aliphatic lacquer for wooden floors

Description

CHIM TABU INDUSTRIA is a two-component aliphatic polyurethane lacquer with special UV ray-absorbing elements. It is non-yellowing, scratch-resistant and features surface hardness and transparency. Due to its chemical and physical characteristics, CHIM TABU INDUSTRIA gives the dry lacquer's film a pleasing appearance. Uses: finish coat for varnishing coloured and/or dyed wood floors.

Characteristics

Mixture ratio	25% CHIM TABU INDUSTRIA Comp.B
Application temperature	+10°C ÷ +25°C
Application	spray / curtein coater
Thinning (if necessary)	DILUENTE DMC 50
Coverage	100 g/m²
Dust dry	30' (1)
Fingerprint dry	2 h (1)
Pot-Life	3-4 h (1)
Sanding	24 h (1)
Gloss level	5 / 10 / 25 gloss (2)
Chemical and physical characteristics	good
Coating	good
Storage stability	1 year (3)
Packaging	12,5 Kg (10 + 2,5) , 25 Kg (20 + 5)
Tool cleaning	DILUENTE DNE

1 *at 20°C and 65% R.H.*
2 *onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days*
3 *in original sealed containers at temperatures between +10°C and +25°C*

How to use

Shake well before use.

When catalysed in the indicated ratios and thinned by 25% with DILUENTE DMC 50, CHIM TABU INDUSTRIA is recommended as a final coat in the subsequent non-yellowing varnish cycle.

* CHIM TABU PRYMER
* wait 6 h without sanding
* CHIM TABU FD
* wait 12/24 h, then sand with 150/180-grit sandpaper
* CHIM TABU INDUSTRIA

Use VELUREX Polish WT, VELUREX Metal Lack or VELUREX METAL MATT for normal upkeep and/or extraordinary maintenance of the floor (see technical data sheets).

Label elements

· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:

http://www.chimiver.com/tds/EN_CHIM_TABU_INDUSTRIA.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.

CHIMIVER PANSERI S.p.A. | Via Bergamo, 1401 | 24030 Pontida (BG) | ITALY | Tel: +39 035 795031 | Fax: +39 035 795556 | chimiver.com | info@chimiver.com
All rights reserved. Any reproduction is forbidden without authorization.