

Technical Datasheet

Item Code: DAPA000X | Rev.: 29-06-2022 | Ver: 3.2

DILUENTE APA

Adhesion promoter for ceramic surfaces



¤Description

DILUENTE APA, single-component product formulated with special resins able to improve adhesion of silanes/epoxy/epoxy-polyurethane adhesive and lacquer to glass, enameled, ceramic or metallic surfaces.**** Destinations:** Adhesion booster.

¤Characteristics	
Mixture ratio	single-component
Application temperature	+10°C ÷ +25°C
Application	cloth
Thinning (if necessary)	DILUENTE ACETONE - DILUENTE DMC 50
Coverage	20-40 g/m² depending on the subfloor and use.
Storage stability	1 year ⁽¹⁾
Packaging	10 L - 5 L - 1 L
Tool cleaning	DILUENTE ACETONE - DILUENTE DMC 50

in original sealed containers at temperatures between +10°C and +25°C

#How to use

After having thoroughly cleaned and degreased the surface, rub the subfloor carefully with a cloth soaked in DILUENTE APA and proceed to spread the adhesive/lacquer as soon as the surface is dry. We recommend treating small areas at a time for optimum results. Allow maximum 30 minutes to pass between applying DILUENTE APA and spreading the adhesive.

¤Label elements



· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

¤Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_DILUENTE_APA.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.