

Technical Datasheet

Item Code: EPRI120A | Rev.: 24-05-2023 | Ver: 3.3

ECOPRIME HS 120

Two-component polyurethane-acrylic water-based primer for wooden floors



Description

ECOPRIME HS 120 is a two-component water-based primer suggested as first coat of wooden floors water-based cycles. Thanks to the high solid content, ECOPRIME HS 120 has high coverage properties, filling the pore of the wood just with a single coat.

Characteristics

Mixture ratio	5/1
Application temperature	+10°C ÷ +25°C
Application	8 mm microfiber roller / flat brush
Thinning (if necessary)	DILUENTE DR H2O
Coverage	80-120 g/m ²
Dust dry	45' ⁽¹⁾
Fingerprint dry	1 h 30' ⁽¹⁾
Pot-Life	1 h 30' ⁽¹⁾
Sanding	12-24 h ⁽¹⁾
Wood oxidation	excellent
Pore filling	excellent
Storage stability	1 year ⁽²⁾
Packaging	6 L (5+1)
Tool cleaning	DILUENTE DNH 40 (with fresh product)

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

ECOPRIME HS 120 catalysed according to the indicated ratio and mixed uniformly, should be applied on wooden floors which have been filled, sanded (120/150 paper grit) and thoroughly vacuumed. When working conditions are critical, it is advisable to add 5-10% of retardant DILUENTE DR H2O (see technical data sheet).

When dry, the surface might have a slightly shiny finishing, due to the high coverage of ECOPRIME HS 120. After 24 hours, previous sanding with 220 paper grit, apply the finish, such as ECOSTAR 2K, ECOWOOD 2K or ECOTRAFFIK 2K (see relative technical sheets).

Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_ECOPRIME_HS_120.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.