

Technical Datasheet

Item Code: FFAC000A | Rev.: 13-09-2023 | Ver: 3.4

FINITURA ACR-00 GN

Two-component acrylic solvent-based varnish for wooden floors



Description

FINITURA ACR-00 GN is a two-component solvent-based acrylic paint. FINITURA ACR-00 GN, due to its chemical and physical characteristics, when used as primer / finish, gives the treated floor a pleasant natural effect.

Characteristics

Mixture ratio	10% INDURITORE ACR-00
Application temperature	+10°C ÷ +25°C
Application	spray / curtain coater
Thinning (if necessary)	DILUENTE DMC 250
Coverage	100-120 g/m ²
Dust dry	10' ⁽¹⁾
Fingerprint dry	10' ⁽¹⁾
Pot-Life	7 h ⁽¹⁾
Sanding	12 h ⁽¹⁾
Gloss level	3 Gloss ⁽²⁾
Chemical and physical characteristics	good
Coating	good
Storage stability	1 year ⁽³⁾
Packaging	11 L (10 + 1) , 27,5 L (25 + 2,5)
Tool cleaning	DILUENTE DNE

1 at 20°C and 65% R.H.

2 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days

3 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

FINITURA ACR-00 GN must be catalysed at 10% with INDURITORE ACR-00 and eventually thinned with DILUENTE DMC 250.

NATURAL EFFECT CYCLE:

- * FINITURA ACR-00 GN
- * wait 12-24 h, then sand using 320 grit abrasive paper
- * FINITURA ACR-00 GN

NATURAL EFFECT CYCLE WITH HIGH TRAFFIC RESISTANCE

- * FINITURA ACR-00 GN
- * wait 4-8h
- * FINITURA ACR-00 GN
- * wait 12-24h, then sand using 320 grit abrasive paper
- * FINITURA ACR-771 G05 (see technical data sheets)

MAINTENANCE:

Ordinary and / or extraordinary maintenance of floors treated with FINITURA ACR-00 GN must be done with the products of the VELUREX line (see technical data sheets).

Warnings

FINITURA ACR-00 GN is to be used only on oak and / or light woods. You can use FINITURA ACR-00 GN on reagents. Always carry out preliminary tests.

Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.