

Technical Datasheet

Item Code: FIAC015A | Rev.: 13-09-2023 | Ver: 3.5

FINITURA ACR M30

Two-component acrylic solventborne lacquer for high traffic wooden floors



Description

FINITURA ACR M30 is a two-component acrylic solvent lacquer whose main characteristics are the very high abrasion resistance and high traffic resistance.

Characteristics

Mixture ratio	10% INDURITORE ACR M30
Application temperature	+10°C ÷ +25°C
Application	spray / curtain machine
Thinning (if necessary)	DILUENTE DMC 50
Coverage	100 g/m ²
Dust dry	30' ⁽¹⁾
Fingerprint dry	2 h ⁽¹⁾
Pot-Life	3-4 h ⁽¹⁾
Sanding	24 h ⁽¹⁾
Gloss level	5 - 10 Gloss ⁽²⁾
Chemical and physical characteristics	good ⁽²⁾
Coating	good
Storage stability	1 year ⁽³⁾
Packaging	27,5 KG (25 + 2,5)
Tool cleaning	DILUENTE DNE

1 at 20°C and 65% R.H.

2 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days

3 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

FINITURA ACR M30 mixed with INDURITORE ACR M30 and thinned by 25% with DILUENTE DMC 50, is used in the following high traffic varnishing cycle:

- * FINITURA ACR M30
- * wait 12h, then sand with abrasive sandpaper 180/220 grit
- * FINITURA ACR M30

The maintenance of wooden floors treated with FINITURA ACR M30 has to be done with VELUREX range of products (see technical data sheets).

Label elements



For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.