

Technical Datasheet

Item Code: FIDC000A | Rev.: 28-04-2025 | Ver: 3.7

FINITURA DC SV 0024

Two-component acrylic solvent lacquer, with dual-cure technology, for wooden floors.



Description

FINITURA DC SV 0024 is a two-component acrylic solvent lacquer, with double cross-linking (UV + Induratore DC 0018). Suitable for industrial applications, spray or via curtain coater, it allows to obtain a natural effect.

Characteristics

Mixture ratio	5% INDURITORE DC 0018
Application temperature	+10°C ÷ +25°C
Application	spray / curtain machine
Thinning (if necessary)	DILUENTE per VERNICI UV
Coverage	60-100 g/m ²
Pot-Life	3-4 h ⁽¹⁾
Sanding	immediate after UV lamps ⁽¹⁾
Gloss level	5 - 10 - 25 - 60 - 80 Gloss ⁽²⁾
Chemical and physical characteristics	good ⁽²⁾
Storage stability	1 year ⁽³⁾
Packaging	22,5 L (20 + 2,5)
Tool cleaning	DILUENTE DNE

1 at 20°C and 65% R.H.

2 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days

3 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

FINITURA DC SV 0024, mixed with INDURITORE DC 0018 and diluted in the measure of 30% with DILUENTE PER VERNICI UV, is recommended as a final coat in the following painting cycle:

- * FONDO DC SV 0011 (see relative technical data sheet)
- * Flash off ca. 10' 35/40°C
- * UV lamps
- * Sand using 220/320 grit sandpaper
- * FINITURA DC SV 0024
- * Flash off ca. 10' 35/40°C
- * UV lamps

As an alternative to FONDO DC SV 0011, you can give two coats of FINITURA DC SV 0024.

The ordinary and/or extraordinary maintenance of the floors treated with FINITURA DC SV 0024 must be done with the products of the VELUREX line (see related technical data sheets).

Label elements



For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.