

Technical Datasheet

Item Code: VEUV060X | Rev.: 14-09-2023 | Ver: 3.5

FINITURA UV R79

UV Primer-Finish based on special acrylic resins



¤Description

Single-component photoactivated product based on special acrylic resins, used in 2-3 coats for varnishing of wooden floors, furniture, doors and panels. It's characterized by excellent hardness, thermal expansion and uniformity of gloss.

#Characteristics	
Preparation	photoactivated
Thinning (if necessary)	DILUENTE MONOMERICO
Application temperature	+10°C ÷ +25°C
Viscosity	40" - 50" Ford Cup 6
Application	single head roller coater / twin
	head roller coater / engraved roller
Coverage	7/15 g/m²
Flash-Off	n.a.
Hardening	2/3 mercury lamps 80W cm²
Gloss level	5 gloss
Dry residue	99%
Chemical and physical	excellent
characteristics	
Storage stability	1 year ⁽¹⁾
Packaging	25 KG
Machine cleaning	DILUENTE ACETONE
	•••••

in original sealed containers at temperatures between +10°C and +25°C

#How to use

Shake well before use.

FINITURA UV R79 is a UV finisher suitable for application by roller machine such as baby and roller laser. FINITURA UV R79 is used, as a primer-finish, in cycles of 2 or 3 coats to obtain a super opaque effect. The regular and intense maintenance of wooden floors treated with FINITURA UV R79 should be made with the VELUREX products line (see technical data sheet).

¤Label elements



· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.