

Technical Datasheet

Item Code: FOAC002A | Rev.: 26-09-2022 | Ver: 3.2

FONDO ACR-276

Fast drying, non-yellowing two component acrylic primer



Description

FONDO ACR-276 is an acrylic two component fast drying primer. It is leaving the wood extremely natural giving a flat and untreated look.

Characteristics

Mixture ratio	10% INDURITORE ACR-10
Application temperature	+10°C ÷ +25°C
Application	spray / curtain
Thinning (if necessary)	DMC 50 thinner
Coverage	100-120 g/m ²
Dust dry	30' ⁽¹⁾
Fingerprint dry	2 h ⁽¹⁾
Pot-Life	3-4 h ⁽¹⁾
Sanding	24 h ⁽¹⁾
Overcoating without sanding	n.a.
Wood oxidation	n.a.
Pore filling	good
Storage stability	1 year ⁽²⁾
Packaging	25 L (20+5) - 12,5 L (10+2,5)
Tool cleaning	DNE thinner

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

FONDO ACR-276 has to be mixed with 10% of INDURITORE ACR 76 and diluted with 25% of DMC50. It can be applied directly on raw wood or on wood already colored. Before applying the top coat sand with 280/320 paper grit.

Note:

Run an adhesion test when the application of FONDO ACR 214 has to be done on wood already colored.

Label elements



For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.