

Technical Datasheet

Item Code: FODC001A | Rev.: 14-09-2023 | Ver: 3.6

FONDO DC SV 0011

Two-component acrylic solventborne primer, with dual cure technology, for wooden floors.



¤Description

FONDO DC SV 0011 is a two-component acrylic solventborne primer, with double cross-linking (UV + Induritore DC 0018), suitable for industrial applications, spray or curtain coater.

¤Characteristics	
Preparation	5% INDURITORE DC 0018
Application temperature	+10°C ÷ +25°C
Application	Spray / Curtain Coater
Thinning (if necessary)	DILUENTE per VERNICI UV
Coverage	60 - 100 g/m²
Pot-Life	3-4 h
Sanding	Immediate after UV lamps
Chemical and physical	good
characteristics	
Storage stability	1 year ⁽¹⁾
Packaging	22,5 L (20 + 2,5)
Machine cleaning	DILUENTE DNE

in original sealed containers at temperatures between +10°C and +25°C

¤How to use

Shake well before use.

FONDO DC SV 0011, hardened with INDURITORE DC 0018 and diluted in the measure of 30% with DILUENTE PER VERNICI UV, is recommended as a first coat in the following cycle:

- * FONDO DC SV 0011
- * Flash off ca. 10' 35/40°C
- * UV Lamps
- * Sand with 220/320 grit sandpaper
- * FINITURA DC SV 0024 (see relative data sheet)
- * Flash off ca. 10' 35/40°C
- * UV Lamps

Note: after curing, two coats of FINITURA DC SV 0024 can be applied.

¤Label elements



· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.