

## Technical Datasheet

Item Code: STUV215X\_0250 | Rev.: 14-09-2023 | Ver: 3.4

# **FONDO UV R335**

### UV primer based on special acrylic resins

#### **¤**Description

FONDO UV R335 is a photoactivated single-component primer based on special acrylic resins used as a filler primer used to coat wooden floors, furniture, doors, panels, etc. FONDO UV R335 has a very high filling power, excellent flow, good sandability, excellent grip and transparency.

<b>¤Characteristics</b>	
Preparation	photoinitiated
Thinning (if necessary)	DILUENTE MONOMERICO
Application temperature	+10°C ÷ +25°C
Viscosity	110" - 120" D6
Application	single head roller coater / Reverse / engraved roller
Coverage	15 - 80 g/m²
Hardening	1/3 mercury lamps
Dry residue	99%
Sanding	excellent
Storage stability	1 year <sup>(1)</sup>
Packaging	25 KG
Machine cleaning	DILUENTE ACETONE

in original sealed containers at temperatures between +10°C and +25°C

#### **#**How to use

Shake well before use.

FONDO UV R335 is a sandable filler suitable for roller application, reverse and cross-linked coating by means of 1/3 mercury UV lamps. FONDO UV R335 is generally applied over adhesion fillers type PRYMER UV R120 (see relative data sheet). UV PRIMER R335 is over-varnishable, after sanding, with FINITURA UV R77 (see relative data sheet).

#### **¤Label elements**



· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.