

IDRO WAX OIL 2K

Waterbased Wax dispersion with natural effect



Description

IDRO WAX OIL 2K is a super matt waterbased wax dispersion with a natural effect that gives the wooden floors a natural look, enhancing the softness and the natural appearance of the wood grain.

Characteristics

Mixture ratio	bi-component (10/1 INDURITORE UW 110)
Application	spray
Application temperature	+10°C ÷ +25°C
Sanding	24 h ⁽¹⁾
Coverage	70-90 gr/m ²
Gloss level	5 gloss ⁽²⁾
Storage stability	1 year ⁽²⁾
Packaging	27,5 L (25+2,5)
Tool cleaning	DILUENTE DNH 40

- 1 at 20°C and 65% R.H.
- 2 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days
- 2 in original sealed containers at temperatures between +10°C and +30°C

How to use

Apply IDRO WAX OIL 2K on surfaces previously sanded with 150/180 grit paper then proceed with the application of the oil on the untreated wood (free of dust, grease and dirt). LIOS WATER OIL can be mixed with INDURITORE UW 110 in the indicated ratio to increase the resistance to liquids and obtain a more matt effect. For industrial applications the following versions are available: LIOS WATER OIL HV. It is possible to apply, by means of a roll machine, 2/3 coats even in one day (20-30 g/m²), after sanding with 320 grit paper between the various coats, according to the times indicated above.

Shake well before use.

IDRO WAX OIL 2K mixed with INDURITORE UW 110, in the indicated ratio, is applied by means of manual and/ or mechanical spraying systems. Apply 70-90 g/m² of IDRO WAX OIL 2K on wood previously sanded and after 12-24 hours, after sanding, proceed to the application of the second coat. Ordinary and/or extraordinary maintenance of the floors treated with IDRO WAX OIL 2K must be done with the VELUREX line of products (see related data sheets).

Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.