

Technical Datasheet

Item Code: SILA000X | Rev.: 29-06-2022 | Ver: 3.0

SIGIL-LA

Single-component water-based sealant for waterproofing the joints of click wooden floors and laminates systems.



Description

SIGIL-LA is a single-component water-based sealant for waterproofing the joints of click wooden floors and laminates systems. SIGIL-LA prevents the joints swelling due to the presence of high humidity levels as in kitchens and bathrooms.

Characteristics

Mixture ratio	single-component
Application temperature	+10°C ÷ +25°C
Application	bottle with pouring lip
Pot-Life	n.a.
Maximum open time	10' ⁽¹⁾
Hardening	24-48 h h
Coverage	30-40 g/linear m (depending of the thickness and wideness of the joints)
Colour	transparent
Storage stability	1 year ⁽²⁾
Packaging	0,5 L
Tool cleaning	Water (before the hardening of the adhesive)

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

Apply SIGIL-LA on the male of the element using the pouring lip, immediately couple making a light pressure to improve a continuous sealing.

Use a wet cotton cloth to remove SIGIL-LA when still fresh, remove the excess by peeling or with a plastic trowel after complete hardening.

Be carefull when cleaning, do not scratch or ruin the floor.

The maintenance of treated with SIGIL-LA has done with VELUREX range of products (see technical data sheets).

Notes: SIGIL-LA is easy to apply, once dry it becomes transparent.

It is advisable to wait at least 12-24 hours before heavy traffic, the complete hardening of the product will be reached within 24-48 hours.

Keep away from frost.

Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_SIGIL-LA.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.