

Technical Datasheet

Item Code: VRPM000X | Rev.: 29-06-2022 | Ver: 4.2

VELUREX Re-Pair

Protective treatment for the extraordinary maintenance of wood, resin and resilient floors





¤Description

VELUREX Re-Pair is a polyurethane resin-based product suitable for the extraordinary maintenance of particularly damaged and subject to heavy traffic resin and resilient flooring such as LVT, PVC and linoleum. If applied on UV varnished wooden floors it is recommended to carry out a preliminary test, and checking the adhesion. VELUREX Re-Pair grants the treated surface a new look characterized by the following properties: surface hardness, toughness and transparency.

¤Characteristics

| Application temperature | +10°C ÷ +25°C |
|--|---|
| Application | Microfiber cloth/Base Mop Clean |
| Thinning (if necessary) | Do not dilute |
| Coverage | 40-60 m²/L |
| Gloss level | MATT: 15 gloss; LACK: 60 gloss ⁽¹⁾ |
| Storage stability | 1 year ⁽²⁾ |
| Packaging | 1 L |
| Tool cleaning | water |
| 1 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days | |

1 onto wet film of 90 micron hardened at 20°C and 65% R. H. for 7 days

#How to use

Shake well before use. The treated surface must be perfectly clean, dry and free from wax and dust. Clean the surface with VELUREX Cleaner Star, VELUREX Resin Cleaner or VELUREX LVT Cleaner depending on the support and following the instructions in the relative data sheets. Once the treated surface has been cleaned, proceed with the application of VELUREX Re-Pair. Dampen the microfibre cloth slightly with water, pour a small amount of VELUREX Re-Pair on the floor and proceed with the application, taking care to distribute the product evenly without leaving accumulations or excesses.

Notes:

The floor can be treaded on after 2-3 hours. Avoid repositioning furniture and carpets before 12-24 hours. The following washing can be carried out after three days with the relative detergents. It's advisable to carry out a preliminary test to verify adhesion to the substrate.

¤Label elements



· For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

¤Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_Velurex_RE-PAIR.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a pratical test by the user who assumes the full responsability of the final result of his work.

² in original sealed containers at temperatures between +10°C and +25°C